

Danish Indoor Climate Labelling



Testing and labelling criteria Care and maintenance products 2nd edition, January 2018

Reference to General labelling criteria	Property	Requirements
Clause 2	<i>Use(s)</i>	Care and maintenance products for treatment of materials, furniture, interior furnishings etc. e.g. maintenance oils for treatment of wood floors and care products for furniture. Paints, varnishes and lacquers are covered by the testing and labelling criteria for interior building paint.
Clause 5.2	<i>Description of the products</i>	The products must only contain preservatives (and the amount of these) necessary for in-can preservation.
Clause 6.5	<i>Sampling</i>	Unopened retail packages can be sampled for testing whenever appropriate. From products delivered only in large bulk units a representative sample for laboratory testing may be taken in a clean, inert, airtight and closeable container.
Clause 7	<i>Reference room loading factor</i>	The loading factor is laid down in the testing and labelling criteria for the product area for which the care and maintenance product is intended. The loading factor for furniture care and maintenance products is 0.1 m ² /m ³ , corresponding to 3 m ² (e.g. treatment of one tabletop and four chairs).
Clause 7.1	<i>Test specimen preparation</i>	Oils intended for wood floors The substrate e.g. parquet boards are joined in tongue and groove without using glue. The oil is applied according to the guidelines of the supplier. The oil treatment should be carried out on solid, planed and polished beech with a moisture ratio of 9 ± 2%. Oil consumption, application method and hardening conditions should be recorded. The application is carried out by the laboratory so that the testing can be initiated 24 ± 2 hours after application. Products intended for furniture The substrate should be neutral what regards emission, e.g. glass or aluminium plates, or relevant to the product in question. The substrate used should appear from the testing report.
Clause 8.2	<i>Maximum allowed time-value</i>	120 days